

# BAVARIA



ANTI  
MICROBIAL




FIRE  
RETARDANT



PHTHALATE  
FREE



QUICK  
SHIP




C-2401




C-2402



C-2403




C-2404



C-2405



C-2406



C-2407



C-2408

## SPECIFICATIONS

Thickness	: 1.20 mm
Width	: 137 cm
Abrasion	: 50.000 rubs
Composition	: PVC & Woven Polyester
Special Surface Finish	: Nubuck
Usage	: Indoor Upholstery
Repeat	: No

## PERFORMANCE

Flammability	: FMVSS-302
Phthalate Free	: REACH
Anti microbial	: ATCC-147

\* Colors shown are indicative references only and will vary dependent on screen resolution



**HEAD OFFICE : PT. BERKAT UNGGUL PRATAMA**

Komplek Citta Graha, Jl. Panjang No. 26 Blok 2L | Jakarta 11520 - Indonesia | +62 21 5819089

**SHOWROOM : LEDER HAUS**

**JAKARTA** • Komplek Cipete Square, Jl. Cipete Raya 55 No.7 | Jakarta 12410 - Indonesia | +62 21 75900 679

**BANDUNG** • Komplek Batununggal Indah, Jl. Batununggal Indah Raya No. 415 | Bandung 40266 - Indonesia | +62 22 8730 7759

**BALI** • Komplek Istana Kuta Galeria, Jl. Patih Jelantik, Blok PMI No.6 | Kuta, Badung, Bali 80361 - Indonesia | +62361 4752 806

# PATTERN ILLUSTRATION

100 cm



137 cm

## APPLICATIONS



Dining Chair



Office Chair



Sofa



## Test Report

Applicant : PT Berkat Unggul Pratama  
Komplek Citta Graha Jl Panjang No 26  
Blok 2L Kedoya Selatan Kebon Jeruk  
Jakarta Barat

Date : May 11, 2023

Attn : Endang

### Sample description:

One (1) group of submitted sample said to be :

Material Name : **CSL**  
Country of Original : Taiwan  
Buyers Company Name : PT Berkat Unggul Pratama  
Date sample received : Apr 18, 2023  
Testing period : Apr 18, 2023 to May 11, 2023

### Test conducted:

As requested by the applicant, for details please refer to attached pages.

### Conclusion:

Section No.	Test Name	Evaluation
230428004-MT-1-EN.001	Flammability	Conforming

### Remark:

Test subcontracted to Intertek China

FN  
Prepared and checked by:  
For Intertek Indonesia

Made Widyani  
Operation Manager - Testing



Test Report

Report Number: JKTH23001290

TEST ITEMS, METHOD AND RESULTS :

<b>230428004-MT-1-EN.001</b>	<b>Flammability</b>			
<b>Ref. Specs Section</b>	FMVSS 302-2021			
<b>Date Tested</b>	2023-05-06~2023-05-07			
<b>Sample No.</b>	IAS2304280040101-1~IAS2304280040101-5			
<b>Test Method</b>	<p>Sample Preparation Methods: specimens made by customer;          Sample Handling: Temperature 21°C ; Relative humidity50% ; Time 24h ;          Test environment: Temperature 23±2°C ; Relative humidity50±5% .          The test was performed in accordance with FMVSS 302-2021.          Specimens size 356×100×1.2mm, No wires          Gas flame height: 38mm.          Duration for exposure to the flame: 15s.</p>			
<b>Acceptance Criteria</b>	≤102mm/min			
<b>Deviation</b>	None			
<b>Test Results</b>	<b>Sample ID</b>	<b>Burn Length (mm)</b>	<b>Burn Time (s)</b>	<b>Burn Rate (mm/min)</b>
	IAS2304280040101-1	/	/	0
	IAS2304280040101-2	/	/	0
	IAS2304280040101-3	/	/	0
	IAS2304280040101-4	/	/	0
	IAS2304280040101-5	/	/	0
	Burning rate max		0	
<b>Evaluation</b>	Conforming			
<b>Test Instruments</b>	<b>Equipment No.</b>	<b>Equipment Name</b>	<b>Calibration Due Date</b>	
	MENV501	Flammability Chamber	N/A	
	MENV672	Steel ruler	2023-12-26	
	MENV896	Electronic stopwatch	2023-05-26	
	MENV758	Thermocouple thermometer	2023-09-26	
	MENV753	Anemometer	2023-07-31	
<b>Observations &amp; Remarks</b>				
None				
<b>Pictures</b>				

This report shall not be reproduced wholly or in parts without written approval of the laboratory

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Term and Conditions.


For the complete term and condition, please visit : <http://www.intertek.com/terms/>

**PT. Intertek Utama Services** Citrabuana Indoloka Building Telp. (62-21) 391 8584 (Hunting), 391 8574 (Direct), Fax. (62-21) 391 8345  
 Jl. Cikini IV No.2, Gondangdia Hardline Laboratory: Jakarta (62-21) 391 6611, Semarang (62-24) 762 7107 / 762 7325  
 Jakarta 10330, Indonesia Email : [hlcoordinator.indonesia@intertek.com](mailto:hlcoordinator.indonesia@intertek.com) Website: [www.intertek.com](http://www.intertek.com)



Test Report

Report Number: JKTH23001290



\*\*\*\*\*

## END OF THE TEST REPORT ##

*This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>*

This report shall not be reproduced wholly or in parts without written approval of the laboratory

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Term and Conditions.

For the complete term and condition, please visit : <http://www.intertek.com/terms/>

**PT. Intertek Utama Services**

Citrabuana Indoloka Building  
 Jl. Cikini IV No.2, Gondangdia  
 Jakarta 10330, Indonesia

Telp. (62-21) 391 8584 (Hunting), 391 8574 (Direct), Fax. (62-21) 391 8345  
 Hardline Laboratory: Jakarta (62-21) 391 6611, Semarang (62-24) 762 7107 / 762 7325  
 Email : [hlcoordinator.indonesia@intertek.com](mailto:hlcoordinator.indonesia@intertek.com) Website: [www.intertek.com](http://www.intertek.com)

**PT. BERKAT UNGGUL PRATAMA  
KOMPLEK CITTA GRAHA,  
JL. PANJANG NO. 26 BLOK 2L, KEBON JERUK, JAKARTA BARAT**

The following sample(s) was /were submitted and identified by the client as:

Sample Description : CSL Leather  
Client's reference No. : 2210003008  
Batch / Lot. No. : -  
Manufacturer/Vendor : PT. BERKAT UNGGUL PRATAMA  
Buyer's Name : -  
Country of Origin : TAIWAN  
Country of Destination : -  
Sample Receiving Date : February 23, 2022  
Test Performing Period : February 23, 2022 to March 09, 2022  
Test Requested : Selected test (s) as requested by client.  
Test Method(s) and Test Result(s) : Please refer to the next page(s).

Signed for and on behalf of  
PT. SGS Indonesia



**Toto Waluyadi**  
**Hardgood Lab Manager**

This document is issued by the Company subject to its General Conditions of Service printed overleaf, or available on request or accessible at [www.sgs.com/termsandconditions.htm](http://www.sgs.com/termsandconditions.htm) and for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested *and such sample(s) are retained 30 days only.*

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction.

The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted.

**PT. BERKAT UNGGUL PRATAMA  
KOMPLEK CITTA GRAHA,  
JL. PANJANG NO. 26 BLOK 2L, KEBON JERUK, JAKARTA BARAT**

**TEST RESULT**

**Phthalates**

Test Method: ISO 14389: 2014. Analysis was performed by GC-MS.

Test Item	CAS No.	Results
		(mg/kg)
		<b>1</b>
Dibutylphthalate (DBP)	84-74-2	n.d.
Benzylbutylphthalate (BBP)	85-68-7	n.d.
Bis-(2-ethylhexyl)phthalate (DEHP)	117-81-7	124
Diisobutyl phthalate (DIBP)	84-69-5	n.d.
Di-C6-8 branched alkylphthalate (DIHP)	71888-89-6	n.d.
Bis (2-methoxyethyl) phthalate (DMEP)	117-82-8	n.d.
Diisopentylphthalate (DiPP)	605-50-5	n.d.
Di-n-pentylphthalate (DnPP)	131-18-0	n.d.
Di-n-Hexylphthalate (DnHP)	84-75-3	n.d.
Sum of all phthalates	--	124
<b>Conclusion</b>		<b>PASS</b>

Note: n.d. = not detected

\* = exceed the limit

Reporting Limit = 50 mg/kg (each)

**Recommended Max. limit: 1000 mg/kg (Each or Sum)**

Remark: Recommended Max. limit specified by Entry 72 of Regulation (EC) No 1513/2018 amending Annex XVII of REACH Regulation (EC) No 1907/2006.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, or available on request or accessible at [www.sgs.com/termsandconditions.htm](http://www.sgs.com/termsandconditions.htm) and for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested *and such sample(s) are retained 30 days only.*

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction.

The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted.

**PT. BERKAT UNGGUL PRATAMA  
KOMPLEK CITTA GRAHA,  
JL. PANJANG NO. 26 BLOK 2L, KEBON JERUK, JAKARTA BARAT**

### Sample Picture



\*\*\*\*\*End of Report\*\*\*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, or available on request or accessible at [www.sgs.com/termsandconditions.htm](http://www.sgs.com/termsandconditions.htm) and for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested *and such sample(s) are retained 30 days only.*

**WARNING:** The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction.

The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted.



**TEST REPORT**

APPLICANT : PT BERKAT UNGGUL PRATAMA  
KOMPLEK CITTA GRAHA  
JL. PANJANG NO. 26 BLOK 2L, KEDOYA  
SELATAN, KEBON JERUK, JAKARTA BARAT

DATE: FEBRUARY 27, 2023

ATTN : ENDANG MAWARNI S

THE SUBMITTED SAMPLE SAID TO BE:

SAMPLE DESCRIPTION : CSL LEATHER  
COLORS : ALL COLORS  
ORDER/STYLE NO. : ALL STYLE  
BUYERS COMPANY NAME : PT BERKAT UNGGUL PRATAMA  
COUNTRY OF DESTINATION : ALL COUNTRY  
COUNTRY OF ORIGIN : TAIWAN  
TESTING STAGE : PRODUCTION SAMPLE

\*\*\*\*\*

TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGES.

\*\*\*\*\*

CONCLUSION:

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
SUBMITTED SAMPLE	ANTIBACTERIAL ACTIVITY TEST	SEE TEST CONDUCTED

\*\*\*\*\*

REMARK :

Test was subcontracted to Intertek China.

PREPARED AND CHECKED BY:  
FOR INTERTEK INDONESIA

TAUFIQ URAKHMAN  
HARDLINE LAB MANAGER

RT/AK/YP/IS/RM/DH

The report shall not be reproduced wholly or in parts without written approval of the laboratory.  
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.  
For the complete term and condition, please visit: <http://www.intertek.com/terms>



Tests Conducted:

1. Antibacterial Activity Test- Parallel Streak Method (Qualitative)

With reference to 2012 American Association of Textile Chemists and Colorists, Technical Manual, AATCC - 147 Test Method 2011.

Incubation temperature: 37°C.

Incubation period: 18 - 24 hours.

Agar medium: Nutrient agar.

Test culture: Staphylococcus aureus (ATCC 6538).

Klebsiella pneumoniae (ATCC 4352).

Test specimen: 25 X 50mm / rectangular / indicated surface of submitted sample.

Test Item	Result
	1
Staphylococcus aureus (ATCC 6538)	No growth was observed directly underneath the tested specimen. with *clearzone 0 mm.
Klebsiella pneumoniae (ATCC 4352)	No growth was observed directly underneath the tested specimen. with *clearzone 0 mm.

\* = Width of clear zone of inhibition belong the edge of the tested specimen.

Sample received condition: Sample in closed plastic bag.

Reference Rating<sup>##</sup>:

Result	Anti-Bacterial Activity
Growth of test miroorganism was observed directly underneath the tested specimen	Not Acceptable
No growth of test miroorganism was observed directly underneath the tested specimen	Acceptable

The report shall not be reproduced wholly or in parts without written approval of the laboratory.

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.

For the complete term and condition, please visit: <http://www.intertek.com/terms>



Test Conducted:

Comment:

Tested sample	Antibacterial activity (AATCC-147)	Result
Tested component of Submitted sample	Against Staphylococcus aureus	Acceptable
	Against Klebsiella pneumoniae	Acceptable

**Component List**

No.	Test Component Description(s)
(1)	CSL Leather

Date Sample Received : January 19, 2023  
 Testing Period : January 19, 2023 to February 27, 2023


\*\*\*\*\*  
 END OF REPORT

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.*

The report shall not be reproduced wholly or in parts without written approval of the laboratory.  
 Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.  
 For the complete term and condition, please visit: <http://www.intertek.com/terms>



PRODUCT PHOTO



The report shall not be reproduced wholly or in parts without written approval of the laboratory.  
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.  
For the complete term and condition, please visit: <http://www.intertek.com/terms>

## CARA PERAWATAN BAHAN KULIT SINTETIK

### ✓ DO's

Apa yang **HARUS** dilakukan



Gunakan lap basah ( lembab )  
berbahan lembut untuk  
membersihkan permukaan bahan



Gosok permukaan bahan secara  
perlahan



Jika terkena noda dengan bahan  
pewarna yang cukup pekat, usahakan  
untuk membersihkan bagian tersebut  
dengan lap basah sesegera mungkin



Apabila ada noda yang masih tertinggal,  
gunakan pembersih khusus kulit sintetik  
untuk membantu menghilangkan noda  
tersebut



Simpan bahan dengan cara digulung  
untuk menghindari bahan kusut  
atau lecek

### ✗ DONT's

Apa yang **TIDAK BOLEH** dilakukan



Jangan gunakan bahan yang  
kasar / tajam ( seperti sikat ) untuk  
membersihkan permukaan kulit



Jangan gunakan produk pembersih  
kimia keras yang dapat merusak  
permukaan kulit seperti :  
pemutih, deterjen, thinner, dll



Tidak menyimpan bahan dengan  
cara dilipat ataupun ditekan dengan  
barang yang berbeban berat untuk  
menghindari terjadinya garis lipatan  
pada bahan



Gulungan roll jangan diletakkan di posisi  
berdiri/vertikal. Gulungan harus diletakkan  
secara horisontal di bidang datar.



Hindari menyimpan bahan kulit di  
tempat yang terkena sinar matahari  
langsung atau bersuhu lembab.

#### Catatan:

Tinta pulpen, spidol permanen, bahan jeans dan bahan berwarna kuat lainnya kemungkinan besar akan sulit atau tidak bisa dibersihkan secara sempurna, terutama pada bahan kulit berwarna terang

