

# Belina



C-4011



C-4022



C-4033



C-4044



C-4055



C-4066




C-4077




C-4088




C-4099




C-4100




C-4101




C-4102



C-4103



C-4104



C-4105



PHTHALATE  
FREE



QUICK  
SHIP

*\* Colors shown are indicative references only and will vary dependent on screen resolution*



LEATHER  
www.csl-leather.com

**HEAD OFFICE : PT. BERKAT UNGGUL PRATAMA**

Komplek Citta Graha, Jl. Panjang No. 26 Blok 2L | Jakarta 11520 - Indonesia | +62 21 5819089

**SHOWROOM : LEDER HAUS**

**JAKARTA** • Komplek Cipete Square, Jl. Cipete Raya 55 No.7 | Jakarta 12410 - Indonesia | +62 21 75900 679

**BANDUNG** • Komplek Batununggal Indah, Jl. Batununggal Indah Raya No. 415 | Bandung 40266 - Indonesia | +62 22 8730 7759

**BALI** • Komplek Istana Kuta Galeria, Jl. Patih Jelantik, Blok PM1 No.6 | Kuta, Badung, Bali 80361 - Indonesia | +62361 4752 806

©2024 Leder Haus. All Rights Reserved.

# PATTERN ILLUSTRATION



## APPLICATIONS



Dining Chair



Office Chair



Sofa

# Belinas

## DESCRIPTION

Italian for beautiful or French for goddess. The collection has long wood grain texture on the surface made in rich earthy bold colors, making it the best leather article to be inserted into any interior designs.

## SPECIFICATIONS

Thickness	1.10 mm
Width	137 cm
Special Surface Finish	Natural Grain
Composition	PVC & Knitted Polyester
Usage	Indoor Upholstery
Repeat	No

## PERFORMANCE

Abrasion	20.000 rubs (ASTM D-4157) 100.000 rubs (ASTM D-4966)
----------	---

## ENVIRONMENTAL SUSTAINABILITY

Phthalate Free	REACH
AZO Dye Free	ISO 14362-1
Formaldehyde Free	ISO 14184-1
Hexavalent Chromium Free	ISO 17075-1

Tensile Strength	ASTM - D751	Warp: 30 kg/3cm, Weft: 20 kg/3cm
Elongation	ASTM - D751	Warp: Max. 100%, Weft: Max. 250%
Tear Strength	ASTM - D2261	Warp: 1.1 kg, Weft: 1.1 kg
Adhesion Strength	ASTM - D751	Warp: 1.1 kg/3cm
Flexibility Strength	ASTM - D2097	400.000 Cycles
Bursting Strength	ASTM - D3786	8.15 kg/cm <sup>2</sup>
Blocking Test	ASTM - D751	Grade 2
Color Fastness Test (Rubbing Test)	AATCC 8	Grade 4

\* The above tests mentioned are guidelines for synthetic leather used in upholstery but do not necessarily indicate its lifespan. When used in different applications, factors such as the quality of craftsmanship, cleaning methods, proper placement, and handling will all impact its durability.

## HOW TO CARE FOR SYNTHETIC LEATHER

### **DO's**

What you **SHOULD** do



Use a soft, damp cloth to clean the surface of the material



Rub the surface slowly with intense



If it is stained with a fairly intense dye, try to clean the area with a damp cloth as soon as possible



If there are stains that are still left behind, use a special cleaner for synthetic leather to help remove the stains

### **DONT's**

What you **SHOULDN'T** do



Do not use rough/sharp materials (such as a brush) to clean the surface



Do not use harsh (chemical) cleaning products such as: bleach, detergent, thinner, and others

#### **Note:**

Ink, permanent marker, denim and other strong textile dyes may be difficult or cannot to remove perfectly, especially on light colored synthetic leather



## Test Report

No.: HTH25300014

DATE: 2025/03/11

PAGE: 1 of 3

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

The following sample(s) was/were submitted and identified by/on behalf of the applicant as :

Sample Description : CSL-SYNTHETIC LEATHER  
Style/Item No. : ALL STYLE

=====  
Sample Receiving Date : 2025/03/05  
Testing Period : 2025/03/05 to 2025/03/11

Test Requested : The test was specified by client, please refer to the result table(s) for details.

Test Result(s) : Please refer to next page(s).

  
Singh Hsiao / Asst. Manager  
Signed for and on behalf of  
SGS TAIWAN LTD.  
Chemical Laboratory - Taipei



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

# Test Report

No.: HTH25300014

DATE: 2025/03/11

PAGE: 2 of 3

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

## Test Part Description

No.1 : Green synthetic leather with gray fabric backing

## Test Result(s)

Test Item(s)	Method	Unit	RL	Result
				No.1
Dibutyl phthalate (DBP) ( CAS No.84-74-2 )	With reference to ISO 14389:2022. Analysis was performed by GC-MS.	mg/kg	30	n.d.
Butyl benzyl phthalate (BBP) ( CAS No.85-68-7 )		mg/kg	30	n.d.
Bis(2-ethylhexyl) phthalate (DEHP) ( CAS No.117-81-7 )		mg/kg	30	n.d.
Diisobutyl phthalate (DIBP) ( CAS No.84-69-5 )		mg/kg	30	n.d.
1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich (DIHP) ( CAS No.71888-89-6 )		mg/kg	30	n.d.
Diisopentyl phthalate (DIPP) ( CAS No.605-50-5 )		mg/kg	30	n.d.
Di-n-hexyl phthalate (DNHP) ( CAS No.84-75-3 )		mg/kg	30	n.d.
Bis(2-methoxyethyl) phthalate (DMEP) ( CAS No.117-82-8 )		mg/kg	30	n.d.
Di-n-pentyl phthalate (DNPP) ( CAS No.131-18-0 )	Method: With reference to ISO 14389 method. Analysis was performed by GC/MS.	mg/kg	30	n.d.

## Note:

1. mg/kg = ppm ; 0.1% = 1000 ppm
2. RL = Reporting Limit
3. n.d. = Not Detected = Less than RL
4. The testing item(s) was/were subcontracted to SGS Taiwan Ltd. Chemical Laboratory – Kaohsiung.
5. The report is invalid if it is partly reproduced or used.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

## Test Report

No.: HTH25300014

DATE: 2025/03/11

PAGE: 3 of 3

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

\* The tested sample / part is marked by an arrow if it's shown on the photo. \*

### HTH25300014



Appearance of the sample-Front view

### HTH25300014



Appearance of the sample-Back view

**\*\* End of Report \*\***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.