


FUTURA




FPG-5111




FPG-5112




FPG-5113




FPG-5114



FPG-5115



FPG-5116



FPG-5117



FPG-5118



FPG-5119



ANTI
MICROBIAL



ANTI
MILDEW



ANTI
UV



FIRE
RETARDANT



PHTHALATE
FREE



QUICK
SHIP

** Colors shown are indicative references only and will vary dependent on screen resolution*

PATTERN ILLUSTRATION



APPLICATIONS



Dining Chair



Office Chair



Sofa

FUTURA

DESCRIPTION

The collection of versatile textile looks and the full spectrum of colors is bringing us into a biased future of synthetic leather and fabric combined. Thanks to its antimicrobial, anti-UV, anti-mold, and extreme durability, the upholstery is very ideal for sitting in healthcare and resort hotels that need clean spaces for guests and a hygienic environment for patients.

SPECIFICATIONS

Thickness	1.20 mm
Width	137 cm
Special Surface Finish	Fabric Look
Composition	PVC & Woven Polyester
Usage	Indoor Upholstery
Repeat	No

PERFORMANCE

Abrasion	53.000 rubs
Flammability	FMVSS-302
Phthalate Free	REACH
Anti Microbial	AATCC - 147
Anti Mildew	ASTM G-21
UV Resistant	ASTM G-154

Abrasion	ASTM - D4966	53.000 rubs
Tensile Strength	ASTM - 2209	Warp: 12.42 kg/3 cm, Weft: 17.66 kg/3 cm
Elongation	ASTM - 2209	Warp: 19%, Weft: 39%
Tear Strength	ASTM - 2261	Warp: 3.45 kg, Weft: 3.05 kg
Adhesion Strength	ASTM - D751	Warp: 3.61 kg/3 cm, Weft: 3.23 kg/3 cm
Flexibility Strength	ASTM - D6182	Warp: 10.000 Times/Grade 5, Weft: 10.000 Times/Grade 5
Bursting Strength	ASTM - D3786	9.2 kg/cm ²
Blocking Test	ASTM - D751	Grade 5
Color Fastness Test (Rubbing Test)	AATCC 8	Dry: Grade 5, Wet: Grade 5

* The above tests mentioned are guidelines for synthetic leather used in upholstery but do not necessarily indicate its lifespan. When used in different applications, factors such as the quality of craftsmanship, cleaning methods, proper placement, and handling will all impact its durability.



THE LEATHER SPECIALIST

HOW TO CARE FOR SYNTHETIC LEATHER

DO's

What you **SHOULD** do



Use a soft, damp cloth to clean the surface of the material



Rub the surface slowly with intense



If it is stained with a fairly intense dye, try to clean the area with a damp cloth as soon as possible



If there are stains that are still left behind, use a special cleaner for synthetic leather to help remove the stains

DONT's

What you **SHOULDN'T** do




Do not use rough/sharp materials (such as a brush) to clean the surface



Do not use harsh (chemical) cleaning products such as: bleach, detergent, thinner, and others

Note:

Ink, permanent marker, denim and other strong textile dyes may be difficult or cannot to remove perfectly, especially on light colored synthetic leather



Test Report

Applicant: PT BERKAT UNGGUL PRATAMA
KOMPLEK CITTA GRAHA
JL. PANJANG NO. 26 BLOK 2L, KEDOYA
SELATAN, KEBON JERUK, JAKARTA BARAT
ATTN: ENDANG MAWARNI S

Number : TWNC01344954

Date Issued : Mar 14, 2025

Sample Description:

One (1) group of submitted samples said to be :

Sample Description	: CSL - SYNTHETIC LEATHER
Order/Style No.	: ALL STYLE
Buyers Company Name	: PT BERKAT UNGGUL PRATAMA
Country of Destination	: All Country
Country of Origin	: Taiwan
Testing Stage	: Production Sample
Date Sample Received	: Mar 04, 2025
Date Test Started	: Mar 04, 2025

Test Conducted:

As requested by the applicant, for details please refer to attached pages.

Authorized By:
On behalf of Intertek Testing Services
Taiwan Limited

Anna Jing
Assistant General Manager



Signed by:

Thomas Chou
Thomas Chou
Manager



Page 1 of 3

Intertek Testing Services Taiwan Ltd.

8F., No. 423, Ruiguang Rd., Neihu District, Taipei 114690, Taiwan, R.O.C.

全國公證檢驗股份有限公司

114690 台北市內湖區瑞光路 423 號 8 樓

Tel: (+886-2) 6602-2888 · 2797-8885 Fax: (+886-2) 6602-2405



Test Conducted :

1. Antibacterial Activity Test

As per AATCC TM147-2011(2016)e

Test Organism : *Staphylococcus aureus* (ATCC 6538)
Klebsiella pneumoniae (ATCC 4352)

Sterilization Of Sample Before Test : No Sterilization

Incubation Temperature : 37±2°C

Incubation Period : 18 - 24 Hours

Agar Medium : Nutrient Agar

Tested Sample Size : 25×50mm

Result :

<u>Test Organism</u>	<u>Test Side</u>	<u>Result</u>
<i>Staphylococcus aureus</i> (ATCC 6538)	Green side	Inhibition of growth beneath the specimen only. (Without clear zone)
<i>Klebsiella pneumoniae</i> (ATCC 4352)	Green side	Inhibition of growth beneath the specimen only. (Without clear zone)


Remark : Clear zone = Clear area of no growth of a microorganism

<u>As per applicant's provide Reference Rating</u>	
<u>Result</u>	<u>Anti-Bacterial Activity</u>
Growth of test miroorganism was observed directly underneath the tested specimen	Not Acceptable
No growth of test miroorganism was observed directly underneath the tested specimen	Acceptable

Comment:

<i>Staphylococcus aureus</i> (ATCC 6538)	Acceptable
<i>Klebsiella pneumoniae</i> (ATCC 4352)	Acceptable





End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek-twn.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

Reporting Statements of Conformity: Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.



TEST REPORT

Report No. : HL30436/2023

Page : 1 of 2

Date : APR. 18, 2023

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK,
JAKARTA BARAT

The following merchandise was submitted and identified by the applicant as:

Product Description: CSL (Durango, Futura)Style/Item No.: ALL STYLECountry of Origin: TAIWAN

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested: UV ResistanceTest Method and Results: ---See following sheet(s)---Date of Receipt: MAR. 30, 2023Testing Period: MAR. 30, 2023 ~ APR. 18, 2023Signed for and on behalf of
SGS Taiwan Ltd.Brian Huang
Supervisor

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TEST REPORT

Report No. : HL30436/2023

Page : 2 of 2

Test Method and Results:

PART NAME No. 1 : Brown fabric

Test Result :

Test Item	Test Method	Test Result
UV Resistance a. Gray Scale (After Test)	ASTM G154-16/ ASTM D2616-19	4.5

Remark: 1. Test Equipment : Accelerated Weathering Tester/ Q-LAB/QUV/ SE.

2. Test Condition :


Lamp : UVA-340

Typical Irradiance : 0.89 W/m²/nm at 340 nmExposure Cycle : 8 hours UV at (60±3) °C Black Panel Temperature,
4 hours Condensation at (50±3) °C Black Panel Temperature

Exposing duration : 200 hours

Notes:

1. As per client's requested, test specified face only.
2. The content of this report is invalid if it is not presented as the entire report.
3. The test was conducted at SGS Taiwan Ltd. Material and Engineering Laboratory-Taipei.

– Pictures –

---End of Report---

Test Report

No.: HTH25300014

DATE: 2025/03/11

PAGE: 1 of 3

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

The following sample(s) was/were submitted and identified by/on behalf of the applicant as :

Sample Description : CSL-SYNTHETIC LEATHER
Style/Item No. : ALL STYLE

Sample Receiving Date : 2025/03/05
Testing Period : 2025/03/05 to 2025/03/11

Test Requested : The test was specified by client, please refer to the result table(s) for details.

Test Result(s) : Please refer to next page(s).


Singh Hsiao / Asst. Manager
Signed for and on behalf of
SGS TAIWAN LTD.
Chemical Laboratory - Taipei



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Test Report

No.: HTH25300014

DATE: 2025/03/11

PAGE: 2 of 3

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

Test Part Description

No.1 : Green synthetic leather with gray fabric backing

Test Result(s)

Test Item(s)	Method	Unit	RL	Result
				No.1
Dibutyl phthalate (DBP) (CAS No.84-74-2)	With reference to ISO 14389:2022. Analysis was performed by GC-MS.	mg/kg	30	n.d.
Butyl benzyl phthalate (BBP) (CAS No.85-68-7)		mg/kg	30	n.d.
Bis(2-ethylhexyl) phthalate (DEHP) (CAS No.117-81-7)		mg/kg	30	n.d.
Diisobutyl phthalate (DIBP) (CAS No.84-69-5)		mg/kg	30	n.d.
1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich (DIHP) (CAS No.71888-89-6)		mg/kg	30	n.d.
Diisopentyl phthalate (DIPP) (CAS No.605-50-5)		mg/kg	30	n.d.
Di-n-hexyl phthalate (DNHP) (CAS No.84-75-3)		mg/kg	30	n.d.
Bis(2-methoxyethyl) phthalate (DMEP) (CAS No.117-82-8)		mg/kg	30	n.d.
Di-n-pentyl phthalate (DNPP) (CAS No.131-18-0)	Method: With reference to ISO 14389 method. Analysis was performed by GC/MS.	mg/kg	30	n.d.

Note:

1. mg/kg = ppm ; 0.1% = 1000 ppm
2. RL = Reporting Limit
3. n.d. = Not Detected = Less than RL
4. The testing item(s) was/were subcontracted to SGS Taiwan Ltd. Chemical Laboratory – Kaohsiung.
5. The report is invalid if it is partly reproduced or used.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Test Report

No.: HTH25300014

DATE: 2025/03/11

PAGE: 3 of 3

PT BERKAT UNGGUL PRATAMA

KOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON JERUK, JAKARTA BARAT

* The tested sample / part is marked by an arrow if it's shown on the photo. *

HTH25300014



Appearance of the sample-Front view

HTH25300014



Appearance of the sample-Back view

**** End of Report ****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Test Report

Applicant: PT BERKAT UNGGUL PRATAMA
KOMPLEK CITTA GRAHA
JL. PANJANG NO. 26 BLOK 2L, KEDOYA
SELATAN, KEBON JERUK, JAKARTA BARAT
ATTN: ENDANG MAWARNI S

Number : TWNC01344958

Date Issued : Apr 17, 2025

Sample Description:

One (1) group of submitted samples said to be :

Sample Description	: CSL (DURANGO, FUTURA, ZIG ZAG)
Order/Style No.	: ALL STYLE
Buyers Company Name	: PT BERKAT UNGGUL PRATAMA
Country of Destination	: All Country
Country of Origin	: Taiwan
Testing Stage	: Production Sample
Date Sample Received	: Mar 04, 2025
Date Test Started	: Mar 04, 2025

Test Conducted:


As requested by the applicant, for details please refer to attached pages.

Authorized By:
On behalf of Intertek Testing Services
Taiwan Limited


Anna Jing
Assistant General Manager



Signed by:


Thomas Chou
Manager



Page 1 of 3

Intertek Testing Services Taiwan Ltd.

8F., No. 423, Ruiguang Rd., Neihu District, Taipei 114690, Taiwan, R.O.C.

全國公證檢驗股份有限公司

114690 台北市內湖區瑞光路 423 號 8 樓

Tel: (+886-2) 6602-2888 · 2797-8885 Fax: (+886-2) 6602-2405



Test Conducted :

1. Mould Resistance Test

With Reference To ASTM G21-15 (2021)e1.

Mould Culture Used : *Aspergillus brasiliensis* (ATCC 9642)
Talaromyces pinophilus (ATCC 11797)
Chaetomium globosum (ATCC 6205)
Trichoderma virens (ATCC 9645)
Aureobasidium pullulans (ATCC 15233)

Culture Medium : Nutrient-Salts Agar

Incubation Period : 28 Days

Incubation Temperature : 28°C

Test Specimen : Submitted samples (2 × 2 inch)

Result :


Obverse side

Rating* At The Specific Period Of Incubation (Day)			
<u>7th</u>	<u>14th</u>	<u>21st</u>	<u>28th</u>
0	0	0	0

Remark : * = Rating scale ranking from 0 to 4 and each number represents the degree of mould growth observed on the specimen surface.

- 0 - None (no growth on specimen surface)
- 1 - Traces of growth (less than 10%)
- 2 - Light growth (10%-30%)
- 3 - Medium growth (30%-60%)
- 4 - Heavy growth (60% to complete coverage)





End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek-twn.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

Reporting Statements of Conformity: Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.



Page 3 of 3

Intertek Testing Services Taiwan Ltd.

8F., No. 423, Ruiguang Rd., Neihu District, Taipei 114690, Taiwan, R.O.C.

全國公證檢驗股份有限公司

114690 台北市內湖區瑞光路 423 號 8 樓

Tel: (+886-2) 6602-2888 · 2797-8885 Fax: (+886-2) 6602-2405



Test Report

Applicant : PT Berkas Unggul Pratama
Komplek Citta Graha Jl Panjang No 26
Blok 2L Kedoya Selatan Kebon Jeruk
Jakarta Barat

Date : May 11, 2023

Attn : Endang

Sample description:

One (1) group of submitted sample said to be :

Material Name : CSL
Country of Original : Taiwan
Buyers Company Name : PT Berkas Unggul Pratama
Date sample received : Apr 18, 2023
Testing period : Apr 18, 2023 to May 11, 2023

Test conducted:

As requested by the applicant, for details please refer to attached pages.

Conclusion:

Section No.	Test Name	Evaluation
230428004-MT-1-EN.001	Flammability	Conforming

Remark:

Test subcontracted to Intertek China

FN
Prepared and checked by:
For Intertek Indonesia



Made Widyani
Operation Manager - Testing



Test Report

Report Number: JKTH23001290

TEST ITEMS, METHOD AND RESULTS:

230428004-MT-1-EN.001	Flammability			
Ref. Specs Section	FMVSS 302-2021			
Date Tested	2023-05-06~2023-05-07			
Sample No.	IAS2304280040101-1~IAS2304280040101-5			
Test Method	Sample Preparation Methods: specimens made by customer; Sample Handling: Temperature 21°C ; Relative humidity50% ; Time 24h ; Test environment: Temperature 23±2°C ; Relative humidity50±5% . The test was performed in accordance with FMVSS 302-2021. Specimens size 356×100×1.2mm,No wires Gas flame height: 38mm. Duration for exposure to the flame: 15s.			
Acceptance Criteria	≤102mm/min			
Deviation	None			
Test Results	<u>Sample ID</u>	<u>Burn Length (mm)</u>	<u>Burn Time (s)</u>	<u>Burn Rate (mm/min)</u>
	IAS2304280040101-1	/	/	0
	IAS2304280040101-2	/	/	0
	IAS2304280040101-3	/	/	0
	IAS2304280040101-4	/	/	0
	IAS2304280040101-5	/	/	0
	Burning rate max	0		
Evaluation	Conforming			
Test Instruments	Equipment No.	Equipment Name	Calibration Due Date	
	MENV501	Flammability Chamber	N/A	
	MENV672	Steel ruler	2023-12-26	
	MENV896	Electronic stopwatch	2023-05-26	
	MENV758	Thermocouple thermometer	2023-09-26	
	MENV753	Anemometer	2023-07-31	
<u>Observations & Remarks</u>				
None				
<u>Pictures</u>				

This report shall not be reproduced wholly or in parts without written approval of the laboratory

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Term and Conditions.

For the complete term and condition, please visit : <http://www.intertek.com/terms/>

PT. Intertek Utama Services


Citrabuana Indoloka Building
Jl. Cikini IV No.2, Gondangdia
Jakarta 10330, Indonesia

Telp. (62-21) 391 8584 (Hunting), 391 8574 (Direct), Fax. (62-21) 391 8345
Hardline Laboratory: Jakarta (62-21) 391 6611, Semarang (62-24) 762 7107 / 762 7325
Email : hlcoordinator.indonesia@intertek.com Website: www.intertek.com



Test Report

Report Number: JKTH23001290



END OF THE TEST REPORT

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>

This report shall not be reproduced wholly or in parts without written approval of the laboratory

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Term and Conditions.

For the complete term and condition, please visit : <http://www.intertek.com/terms/>

PT. Intertek Utama Services

Citrabuana Indoloka Building
Jl. Cikini IV No.2, Gondangdia
Jakarta 10330, Indonesia

Telp. (62-21) 391 8584 (Hunting), 391 8574 (Direct), Fax. (62-21) 391 8345
Hardline Laboratory: Jakarta (62-21) 391 6611, Semarang (62-24) 762 7107 / 762 7325
Email : hlcoordinator.indonesia@intertek.com Website: www.intertek.com

TEST REPORT

Report No. : HU30003/2025

Page : 1 of 2

Date : MAR. 12, 2025

PT BERKAT UNGGUL PRATAMAKOMPLEK CITTA GRAHA, JL. PANJANG NO.26 BLOK 2L, KEDOYA SELATAN, KEBON
JERUK, JAKARTA BARAT**The following merchandise was submitted and identified by the applicant as:**Product Description: CSL-SYNTHETIC LEATHERStyle/Item No.: ALL STYLE**We have tested the submitted sample(s) as requested and the following results were obtained:**Test Requested: For compliance with Federal Motor Vehicle Safety Standard No.302
Flammability of interior materials(49 CFR 571.302).Test Result: ---See following sheet(s)---Date of Receipt: Mar. 04, 2025Testing Period: Mar. 04, 2025 ~ Mar. 12, 2025Signed for and on behalf of
SGS Taiwan Ltd.
Lawrence Yang
Asst. Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TEST REPORT

Report No. : HU30003/2025

Page : 2 of 2

Test Result:

For compliance with Federal Motor Vehicles Safety Standard No.302

PassFlammability of interior materials

	<u>Filling</u>			<u>Warp</u>		
	<u>Char Length</u> (mm)	<u>After Flame</u> (sec.)	<u>Burn Rate</u> (mm/min)	<u>Char Length</u> (mm)	<u>After Flame</u> (sec.)	<u>Burn Rate</u> (mm/min)
1.	0	0	SE	0	0	SE
2.	0	0	SE	0	0	SE
3.	0	0	SE	0	0	SE

Note: SE = Self - Extinguish. The material ignites but extinguishes itself before reaching the 38 mm point from the clamped start of the specimen.

Test Requirement: The burn rate shall not exceed 102 mm per minute.

Conclusion: The submitted sample(s) **complies with** the requirements of Federal Motor Vehicle Safety Standard No. 302 Flammability of interior materials (49 CFR 571.302).

Remark:

1. The content of this report is invalid if it is not presented as the entire report.
2. The decision rule of the statements of conformity is following the ILAC G8:09/2019 by using the simple acceptance decision rule.

- Picture(s) -



Photo A: Appearance of the sample(s)

--- End of Report ---

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.